

»speedfit« and »sharkbite« series – coils.

Plastic pipe made of LLDPE/LDPE with approval according to DVGW work sheet W270, KTW, NSF and WRAS. LLDPE/LDPE pipes are suitable for potable water uses (cold water) with a maximum chlorine content of 4 parts per million (ppm).

Warm water above 20 °C and / or pressurising above the given maximum reduces the lifetime of this material. Also, placement in direct sunlight should be avoided.

Operating temperature -20 °C to 65 °C

| Plastic pipe, LLDPE/LDPE - black | | | | | | | |
|----------------------------------|-----------|--------------------|--------------------|-------------------------|---------------------|------------------------------|----------|
| Art. No. | Type No. | Tube O.D. mm | Tube I.D. mm | Working pressure bar | Reel length m | Bending radius min. mm | Material |
| 136361 | 97.04-100 | 4 | 2.5 | -0.95 to 15 | 100 | 25 | LLDPE |
| 136362 | 97.06-100 | 6 | 4 | -0.95 to 15 | 100 | 25 | LLDPE |
| 136363 | 97.08-100 | 8 | 6 | -0.95 to 10 | 100 | 30 | LLDPE |
| 136364 | 97.10-100 | 10 | 7 | -0.95 to 10 | 100 | 32 | LLDPE |
| 136365 | 97.12-100 | 12 | 9 | -0.95 to 10 | 100 | 63 | LLDPE |
| 136366 | 97.15-100 | 15 | 11.5 | -0.95 to 10 | 100 | 85 | LLDPE |
| 136367 | 97.22-50 | 22 | 17.7 | -0.95 to 6 | 50 | 150 | LDPE |



97.15-100